

PRODUCT DESCRIPTION

A phenolic modified alkyd primer designed for interior and exterior use on steel substrates. Acceptable topcoats include alkyds, acrylics, vinyl, epoxies, and urethanes.

Color: White, Black, Red Oxide, Yellow Oxide, and Gray

Gloss: Flat & Satin (black)

Benefits

Non-lifting

Excellent rust resistance

Easy to use

Weldable

Fast drying

Can be used with various topcoats

PRODUCT AND PERFORMANCE DATA
Product Data

Property	Result
Volume solids (%)	38 ±2
Weight solids (%)	54 ±2
VOC	505 - 543 grams/L 4.21- 4.53 lbs./gallon
Recommended dry film thickness	1.5 – 3 mils
Recommended wet film thickness	3 – 8 mils
Theoretical Coverage (1.0 mil)	609 ft ² /gal

Performance Data

Test Method	Standard	Result
Gloss @ 60°	ASTM D523-14	2 - 15
Adhesion	ASTM D3359	5B
Impact Resistance	ASTM D2794-90	>120 in-lbs

**Testing performed on fully cured 16P900 product*

WELDABILITY

This product can be directly welded over as it contains no heavy metals that would produce toxic fumes. The paint is formulated to minimize the amount of "Burn-Back". Critical, load-bearing welds should be made in accordance with industry standards.

SURFACE PREPARATION
Pre-cleaning:

Clean all surfaces to be coated in accordance with SSPC-SP-1, Solvent Cleaning prior to additional surface preparation or coating application. Surface must be clean, dry and free of any dirt, dust, oil, and all other visible contaminants.

Surface Preparation

Recommended	SSPC SP 6 (commercial blast cleaning)
Minimum	SSPC SP 2 or SP 3 (hand or power tool cleaning)

MIXING AND THINNING
Mix Directions

Stir thoroughly before and occasionally during use.

Thinning Directions

Product packaged ready to apply. If needed thin up to 10% maximum with Toluene or Xylene.

APPLICATION
Application Parameters

Relative Humidity	20% - 70%
Minimum Temperature	50°F (10°C)
Maximum Temperature	80°F (27°C)

Curing Schedule
Alkyd
Polyurethane or Epoxy
Water Base

Dry to topcoat	30 min	1 hour	1 hour
----------------	--------	--------	--------

Application methods

The product can be applied by

Spray

Airless or air assist spray: 0.011 – 0.017 orifice size (in)

Conventional spray: 1.0 – 1.8 orifice size (mm)

*Aerosol touch-up available upon request. Contact your Technical Sales Representative for additional information.

PACKAGING AND STORAGE**Packaging**

1 – Gallon

5 – Gallon

Drums

Storage

The product must be stored in accordance with local and national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 73°F (23 °C) = 12 months *

*When kept in recommended storage condition and original unopened containers.

CAUTION

Adequate health and safety precautions should be observed during storage, handling, use and curing periods.

READ SAFETY DATA SHEETS BEFORE USING THIS PRODUCT

DISCLAIMER

The technical data and suggestions for use in this product data sheet are currently correct to the best of our knowledge, but are subject to change without notice. Because application and conditions vary, and are beyond our control, we are not responsible for results obtained in using this product, even when used as suggested. The user should conduct tests to determine the suitability of the product for the intended use under then existing conditions. Our liability for breach of warranty, strict liability in tort, negligence or otherwise is limited exclusively to replacement of the product or refund of its price. Under no circumstances are we liable for incidental or consequential damages.