

216P Series

Technical Data Sheet

PRODUCT DESCRIPTION

A 3.5 VOC or lower, phenolic modified alkyd universal primer designed for use under multiple topcoats. It may be topcoated with a variety of finish coats such as alkyds, acrylics, vinyl, epoxies, and urethanes.

Color:Black, Red, GraySheen:Flat and Satin (Black)

PRODUCT AND PERFORMANCE DATA

Product Data*

Property	Result		
Volume solids (%)	44 – 48 ± 2		
Weight solids (%)	63 - 66 ± 2		
VOC	409 – 420 g/L ± 2		
Recommended dry film thickness	1.5 – 2.5 mils		
Recommended wet film thickness	3.25 – 5.75 mils		
Theoretical Coverage (1.0 mil)	726 – 770 ft²/gal		

* 216P317 data excluded from product data, see product specific TDS for info

Performance Data *

Test Method	Standard	Result
Adhesion	ASTM D3359	5B
Impact Resistance	ASTM D2794-90	>120 in-lbs
Gloss @ 60°	ASTM D523-14	2 - 15

*Testing performed on fully cured 216P901 product

SURFACE PREPARATION

Pre-cleaning:

Clean all surfaces to be coated in accordance with SSPC-SP-1, Solvent Cleaning prior to additional surface preparation or coating application. Surface must be clean, dry and free of any dirt, dust, oil, and all other visible contaminates.



216P Series

Technical Data Sheet

Surface Preparation

Recommended	SSPC SP 6 (commercial blast cleaning)	
Minimum	SSPC SP 2 or SP 3 (hand or power tool cleaning)	

MIXING AND THINNING

Mix Directions

Stir thoroughly before and occasionally during use.

Thinning Directions

Product packaged ready to apply. If needed thin up to 10% maximum with Xylene or Toluene. (These thinners will add VOCs to your product)

APPLICATION

Application Parameters

Relative Humidity	20%-70%
Minimum Temperature	40°F *
Maximum Temperature	85°F

*temperature must be at least 5° above the dew point during application

Curing Schedule	Alkyd	Polyurethane or Epoxy	Water Base
Dry to recoat	30 min	1 hour	1 hour

Application methods

The product can be applied by

Spray Airless spray: 0.011" - 0.015" Conventional spray: 0.8mm – 1.8mm Brush/Roll Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.

This Technical Data Sheet supersedes those previously issued. <u>www.forrestpaint.com</u> <u>info@forrestpaint.com</u>



216P Series

STORAGE

Storage

The product must be stored in accordance with local and national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 73°F (23 °C) = 12 months *

*When kept in recommended storage condition and original unopened containers.

CAUTION

Adequate health and safety precautions should be observed during storage, handling, use and curing periods. READ SAFETY DATA SHEETS BEFORE USING THIS PRODUCT

DISCLAIMER

The technical data and suggestions for use in this product data sheet are currently correct to the best of our knowledge, but are subject to change without notice. Because application and conditions vary, and are beyond our control, we are not responsible for results obtained in using this product, even when used as suggested. The user should conduct tests to determine the suitability of the product for the intended use under then existing conditions. Our liability for breach of warranty, strict liability in tort, negligence or otherwise is limited exclusively to replacement of the product or refund of its price. Under no circumstances are we liable for incidental or consequential damages.