

# | TECAPRO®



**FIT FOR ANY  
PURPOSE**

**TECAPRO®**  
BD 11 – 230 g/m<sup>2</sup>

## **LIGHT WEIGHT COTTON COMFORT**

Ideal choice for workers evolving in warm environments and climates.

## **HEAT & FLAME PERFORMANCE**

Protects against industrial heat and flame hazards.

## **EXCEPTIONAL VALUE**

Developed to withstand repeated usage as well as domestic and industrial laundering.

# TECAPRO®

TECHNICAL DATA*	TECAPRO®	TEST METHOD
Quality	BD 11	
Width	148 cm (+2/-1 cm)	ISO 22198: 2006
Weight	230 g/m <sup>2</sup> (± 5%)	ISO 3801: 1977
Composition	Cotton 100%	
Construction	3/1 twill	
Available finishes	Standard: Durable flame-retardant finish	
<b>Physical performance</b>		
Tensile strength	1000 N x 450 N (±10%)	ISO 13934-1: 1999
<b>Care labelling</b>		
Domestic laundering		
Industrial laundering	75 °C	
Protection	Flame protection	
PPE requirements†		
<b>CERTIFICATION*</b>		
	Industrial flame & heat hazards	EN ISO 11612 A1, B1, C1, F1; 2015 (A1 = 50 x ISO 15797 - 75 °C)**
	General requirements***	EN ISO 13688: 2013

\* Copyright symbols: NEN, Delft (Netherlands)

\*\* After pre-treatment (according to ISO 15797, 1 wash procedure 8 (75°C) and 1 tumble drying (procedure A) (max. 70 °C outlet temperature).

\*\*\* Tested on specific colours.

## COLOURS

Sapphire 40458	Caledo 47240	Coral 40460
-------------------	-----------------	----------------

Ten Cate Protect B.V. is certified according:



Member of the E.T.S.A.

All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.