

# TECAPRO®



**FIT FOR ANY  
PURPOSE**

**TECAPRO® SATIN LINE**  
**BG 9035 – 350 g/m<sup>2</sup>**

## **EXTREME SOFTNESS AND FLEXIBILITY**

Feels soft and supple thanks to the 4/1 satin construction, high amount of cotton and Comfort-Control finish.













## **OUTSTANDING METAL AND SPARK PROTECTION**







Due to a smooth surface, molten metal splashes and sparks run right off.

## **UNBEATABLE VALUE FOR MONEY**

Retains its strength even after extensive industrial laundering - minimizing cost of ownership.

# TECAPRO®

TECHNICAL DATA	TECAPRO® SATIN LINE	TEST METHOD
Quality	BG 9035	
Width	153 cm (+2/-1 cm)	ISO 3801: 1978
Weight	350 g/m <sup>2</sup> (± 5%)	ISO 3932: 1980
Composition	co/pes/Static-Control™ 79/20/1%	
Construction	4/1 Satin	
Available finishes	Standard: Durable flame-retardant finish with Comfort-Control and Hydro-Tec	
<b>Physical performance</b>		
Tensile strength	1550 N x 600 N (±10%)	ISO 13934-1: 1999
<b>Care labelling</b>		
Domestic laundering	     	To keep these fabrics looking at their best, contact TenCate for laundering, care and maintenance advice.
Industrial laundering	75 °C	
Protection	Multi-risk	
PPE requirements*	     	

CERTIFICATION*		
	Industrial flame & heat hazards	EN ISO 11612 A1,A2,B1,C1,E3,F1: 2015 (A1 + A2= 50 x ISO 15797 - 75 °C)
	Electric Arc	Single layer: EN IEC 61482-1-2, class 1: 2015 HRC/Category 2 (8 ≤ ATPV ≤ 25 cal/cm <sup>2</sup> ) System: BG 9035 + BG 9025 = EN IEC 61482-1-2, class 2: 2015
	Welding	EN ISO 11611, class 1: 2015
	Anti-static for explosion risk	EN 1149-5: 2018, EN 1149-3: 2004
	Liquid chemicals**	EN 13034: 2005 + A1: 2009
	High Visibility colour: Yellow Contrast colours: River 60662, Vulcano 66935, Marmelade 66777, Papaya 61070, Grey 65436, Navy 63805	EN 20471: 2013
	General requirements***	EN ISO 13688: 2013

\* Copyright symbols: NEN, Delft (Netherlands) \*\* Hydro-Tec finish only \*\*\* Tested on specific colours

COLOURS							
River 60662	Navy 63805	Vulcano 66935	Charcoal 65576	Black 60475	HV Yellow 64516	Marmelade 66777	Papaya 61070

Ten Cate Protect B.V. is certified according:



Member of the E.T.S.A.

All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.