



MAKE ANY CONDITION YOUR COMFORT ZONE

COOLER AND DRIER IN ALL SITUATIONS

Tecasafe® Plus provides an excellent moisture management control that keeps the wearer cool and dry at all times.

OUTSTANDING AFTER-WASH APPEARANCE

Featuring Truecolor™ Technology, which provides outstanding after-wash appearance by retaining its original color without fading.

SUPERIOR INHERENT FR PROTECTION

Inherently heat- and flame-resistant fabric that offers excellent protection against multiple high-risk situations, such as flash fire and electric arc.

TECASAFE® PLUS

Multilite™

TECHNICAL DATA	TECASAFE® PLUS Multilite™	TECASAFE® PLUS Multilite™ Truecolor™
Nominal Weight	5.7 osy (195 gsm)	5.5 osy (185 gsm)
Construction	Twill weave	Twill weave
Colors	Gray, Light Blue, Khaki, Orange, Red, Yellow	Navy, Spruce Green
Fiber Content	Modacrylic, Lyocell, Aramid	Modacrylic, Lyocell, Aramid
Certification/Compliant	NFPA 2112, ASTM F1506, EN ISO 11612	NFPA 2112, ASTM F1506, EN ISO 11612

Flame Resistance			
PPE Rating	NFPA 70E	Category 2	Category 2
Electric Arc Rating	ASTM F1959	9.1 cal/cm ²	8.5 cal/cm ²
Predicted Body Burn	NFPA 2112	PASS	PASS
Vertical Flame Initial: After flame Initial: Char length After 100x Wash: After flame After 100x Wash: Char length	ASTM D6413, NFPA 2112	2 sec < 4 in (100 mm) < 2 sec < 4 in (100 mm)	2 sec < 4 in (100 mm) < 2 sec < 4 in (100 mm)
Thermal Shrinkage Initial 3x After Wash	NFPA 2112	< 10% < 10%	< 10% < 10%

Fabric Strength			
Tensile Strength Warp x Fill	ASTM D5034	510 x 400 N	535 x 379 N
Elmendorf Tear Warp x Fill	ASTM D1424	30 N	45 N
Seam Strength	ASTM D434, Force at 0.25 in slippage	155 N	155 N

Comfort/Appearance			
Color Fastness Laundering Shade Change (Score 5: Best to 1:Worst)	AATCC 61 2A	4-5	4-5
Xenon Light Exposure After 20 Hours (Score 5: Best to 1:Worst)	AATCC 16	4	5
Color Fastness to Crocking Dry Wet (Score 5: Best to 1:Worst)	ASTM 3512	5 4-5	5 4-5
Pilling Resistance Initial 60 min (Score 5: Best to 1:Worst)	ASTM 3512	5	4
Air Permeability	ASTM D3787 ASTM D737-96	67 ft ³ /ft ² /min	67 ft ³ /ft ² /min
UV Protection		50+ UPF	50+ UPF

* Appearance depends on shade of fabric.

STANDARD COLOURS				OPTIONAL COLOURS
Gray	Light Blue	Khaki	Orange	TenCate Protective Fabrics, the world's textile dyeing expert, can produce almost every color with a minimum quantity. For more information about color-combination requirements, as well as any other information you may need, please contact us at apacsales@tencatefabrics.com Colors shown here are reference only.
Red	Yellow	Navy	Spruce Green	

All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. Tencate Protective Fabrics declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making. To learn more, visit Asia. TenCateFabrics.com or email to APACSales@tencatefabrics.com