

TECASAFE® PLUS

TechT4™

INHERENT FR PROTECTION IN A LIGHTWEIGHT BASE LAYER

TECASAFE® PLUS Tech T4™
5.0 osy (170 gsm)

SELF-EXTINGUISHING

TECASAFE® PLUS Tech T4™ will not ignite, melt or drip as it enhances the protection of flame-resistant outer layers.

COOLER AND DRIER IN ALL SITUATIONS

Featuring Coolderm™ Technology, which provides an excellent moisture management control that always keeps the wearer cooler and drier without any harsh chemical treatments.

COMFORTABLE WITH PROTECTION

TECASAFE® PLUS Tech T4™ is like an athletic t-shirt with the added bonus of inherent FR protection. It provides wearers the extraordinary softness, comfort, and protection they need beneath their uniforms.

TECASAFE® PLUS

TechT4™

TECHNICAL DATA		TENCATE TECASAFE® PLUS Tech T4™
Nominal Weight		5.0 osy (170 gsm)
Construction		Jersey
Colors		Navy, Midnight Navy, Sand, Black, Gray
Fiber Content		Lyocell, Modacrylic, Nylon
Certification		ASTM 1506
Flame Resistance		
Energy Breakopen Threshold EBT Rating PPE Category	NFPA 70E, ASTM 1959	4.8 cal/cm ² Category 1
Vertical Flame Initial: After flame Initial: Char Length	ASTM 6413	< 2.0 sec < 6.0 in (150 mm)
Physical Testing		
Burst Strength – Ball Method	ASTM D3787	310 N (70 lbf)
Burst Strength – Mullen Method	ASTM D3786	460 kPa (65 psi)
Dimensional Stability	AATCC 135	< 10%
Fabric Stretch and Recovery Fabric Stretch Fabric Recovery	ASTM 6413	24% x 43% 92.5% x 87%
Comfort		
Air Permeability	ASTM D737	165 cc/sec
Appearance		
Color Fastness Laundering Shade Change (Score 5: Best to 1: Worst)	AATCC 61 2A	Up to 4*
Xenon Light Exposure After 20 hours (Score 5: Best to 1: Worst)	AATCC 16	Up to 3-4*
Pilling Resistance Initial: 60 minutes (Score 5: Best to 1: Worst)	ASTM D3512	Up to 4-5*

* Appearance depends on shade of fabric.
Copyright © 2019 TenCate Protective Fabrics

STANDARD COLOURS					OPTIONAL COLOURS
Gray	Sand	Navy	Midnight Navy	Black	TenCate, the world's textile dyeing expert, can produce almost every colour with a minimum quantity of 3000 metres. Smaller quantities can be ordered, subject to a surcharge. For more information about colour-combination requirements, as well as any other information you may need, please contact TenCate.

Any listed data or claims represent typical values. Results from multiple tests unless otherwise stated. TenCate Protective Fabrics assumes no liability whatsoever for the accuracy or completeness of the information contained herein. Users of any substance must satisfy themselves by an independent investigation that the material can be used safely. TenCate Protective Fabrics describes only certain hazards but cannot guarantee these are the only hazards. Content within is subject to change at the sole discretion of TenCate Protective Fabrics. Any images, photography, swatch illustrations or color descriptions appear only as representative and are not intended for color shade matching or the exact size or shape of a weave or knit. Any fabric weights listed are nominal. If any of these matters are of a concern, please speak with your TenCate Protective Fabrics representative.