TECASAFE®PLUS



TECASAFE® PLUS XL 9240 – 240 g/m²

COOLER AND DRIER IN ALL SITUATIONS

Tecasafe® Plus provides an excellent moisture management control that keeps the wearer cool and dry at all times.

OUTSTANDING AFTER-WASH APPEARANCE

Colourfastness rating of 4-5 after 50 industrial washing cycles (ISO 15797).

SUPERIOR INHERENT FR PROTECTION

Inherently heat- and flame-resistant fabric that offers excellent protection against multiple high-risk situations, such as flash fire and electric arc.



TECASAFE®PLUS

TECHNICAL DATA	TECASAFE® PLUS	TEST METHOD
Quality	XL 9240	
Width	152 cm (+2/-1 cm)	ISO 3801: 1978
Weight	240 g/m² (± 5%)	ISO 3932: 1980
Composition	$Modacrylic/lyocell/para-aramid/Static-Control^{\text{TM}}$	
Construction	2/1 twill	
Available finishes	Standard: Hydro-Tec. Optional: Comfort	
Physical performance		
Tensile strength	900 N x 650 N (±10%)**	ISO 13934-1: 1999
Care labelling		
Domestic laundering	₩ X 0 0	
Industrial laundering	75 °C Colour: White:	
PPE requirements*	② ② ☆ ② □ optional:	

^{*} Copyright symbols: NEN, Delft (Netherlands) ** Hydro-Tec finish only

CERTIFICATION			
0	Industrial flame & heat hazards	EN ISO 11612 A1,A2,B1,C1,E2,F1: 2015 (A1 + A2= 100 x ISO 15797 - 75 °C)	
NEW NEW	Short-duration thermal exposures from fire	NFPA 2112: 2018	
	Wildland fire fighting	EN 15614: 2007	
<u> </u>	Welding	EN ISO 11611, class 1: 2015***	
	Electric Arc	Single Layer: EN IEC 61482-1-2, class 1; 2015 HRC/Category 2 (8 ≤ATPV ≥ 25 cal/cm²) System: XL9200 + XL9240 EN IEC 61482-1-2; 2015 class 2 (7kA) System: HRC/Category 2 (8 ≤ATPV ≥ 25 cal/cm²)	
(2)	Anti-Static for explosion risk	EN 1149-5: 2018, EN 1149-3: 2004	
	Liquid chemicals**	EN 13034: 2005 + A1: 2009 EN ISO 20471: 2013	
[<u></u>	High Visibility colour: Yellow Contrast colours are available		
	General requirements***	EN ISO 13688: 2013	
	Öko-Tex Standard 100, class 2	Centexbel, no. 0903009	

^{**} Hydro-Tec finish only *** Although this fabric full-fills the requirements of EN ISO 11611, fabrics out of the Tecasafe® Plus collection are more suitable for welding applications **** Tested on specific colours

COLOURS									
Twilight 89250	Black velvet 89254	Moonmist 89253	Intense blue 89350	Delftblue 89249	Ribbon red 89252	Sunrise Orange 89305	Yellow (EN 20471) 89251		











All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.